



# Komponente - Kunststoffe

UL Geschäftsnummer: E343729

SAX POLYMERS INDUSTRIE GMBH  
LICHTBLAUSTRASSE 8, WIEN 1220 AT



## SAXAMID: 226F5RY01(f2)

Polyamide 66 (PA66), pellets, glass reinforced

(f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.

Brennbarkeit	Wert	Prüfmethode
Entflammbarkeitsklasse - UL		UL 94
0,75 mm, ALL	V-0	IEC 60695-11-10, -20
3,0 mm, ALL	V-0	
Glühdraht-Entflammbarkeitsindex (GWFI)		IEC 60695-2-12
0,75 mm	960 °C	
3,0 mm	960 °C	
Glühdraht-Entzündungstemperatur (GWIT)		IEC 60695-2-13
0,75 mm	725 °C	
3,0 mm	750 °C	
Elektrische Eigenschaften	Wert	Prüfmethode
Hot-wire Ignition (HWI) - Entzündung durch Heißdraht		UL 746
0,75 mm	PLC 0	
3,0 mm	PLC 0	
Hochampere Lichtbogenzündung (HAI)		UL 746
0,75 mm	PLC 0	
3,0 mm	PLC 0	
Vergleichszahl zur Kriechwegbildung (CTI)	PLC 0	UL 746
Thermische Eigenschaften	Wert	Prüfmethode
RTI Elec		UL 746
0,75 mm	140 °C	
3,0 mm	140 °C	
RTI Imp		UL 746
0,75 mm	110 °C	
3,0 mm	110 °C	
RTI Str		UL 746
0,75 mm	140 °C	
3,0 mm	140 °C	
Physikalische Eigenschaften	Wert	Prüfmethode
Eignung für den Einsatz in Außenbereichen	f2	UL 746C



## Notice of Disclaimer

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.